

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently amended) A method of breaking a substrate of brittle material, the method comprising ~~acts of:~~

Deleted: the steps

providing a substrate of a brittle material,

heating the substrate with a laser beam to create a heated spot on the substrate,

moving the laser beam and the substrate with respect to each other to create a line of heated spots on the substrate,

cooling the heated spots on the substrate by locally applying a cooling medium such that a micro-crack in the line of heated spots is propagated ~~on the substrate~~, and

breaking the substrate along the line of the propagated micro-crack by applying a force on the substrate

wherein the cooling medium comprises an aqueous surfactant solution.

2. (Currently amended) ~~The method of breaking a substrate of~~ brittle material according to claim 1, wherein the cooling medium further comprises air mixed with the aqueous surfactant solution.

Deleted: A

3. (Currently amended) ~~The method of breaking a substrate of~~
brittle material according to claim 1, wherein the concentration of
the surfactant is in the range of 0.01 to 1% of weight.

Deleted: A

4. (Currently amended) ~~The method of breaking a substrate of~~
brittle material according to claim 1, wherein the aqueous
surfactant solution comprises a cationic surfactant.

Deleted: A

5. (Currently amended) ~~The method of breaking a substrate of~~
brittle material according to claim ~~4~~, wherein the cationic
surfactant comprises cetyl trimethyl ammonium bromide (CTAB).

Deleted: A

Deleted: 3

6. (Currently amended) ~~The method of breaking a substrate of~~
brittle material according to claim 1, wherein the aqueous
surfactant solution comprises a nonionic surfactant.

Deleted: A

7. (Currently amended) ~~The method of breaking a substrate of~~
brittle material according to claim ~~6~~, wherein the nonionic
surfactant comprises octadecyl deca(ethylenoxide) hydroxide.

Deleted: A

Deleted: 5

8. (Currently amended) ~~The method of breaking a substrate of~~
brittle material according to claim 1, wherein the aqueous
surfactant solution comprises an anionic surfactant.

Deleted: A

9. (Currently amended) ~~The method of breaking a substrate of~~
~~brittle material according to claim 3, wherein the anionic~~
surfactant comprises dodecylbenzene sulfonic acid sodium salt.

Deleted: A

Deleted: 7

10. (Currently amended) ~~The method of breaking a substrate of~~
~~brittle material according to claim 1, wherein the brittle material~~
~~comprises one or more of glass, crystalline silica and ceramics.~~

Deleted: A

Deleted: ,

Deleted: or compositions
thereof.

11. (New) A method of breaking a substrate of brittle material, the
method comprising acts of:

providing a substrate of a brittle material,

heating the substrate with a laser beam to create a heated
spot on the substrate,

moving the laser beam and the substrate with respect to each
other to create a line of heated spots on the substrate,

cooling the heated spots on the substrate by locally applying
an aqueous surfactant solution such that a micro-crack in the line
of heated spots is propagated on the substrate and the aqueous
surfactant solution enters the micro-crack, and

breaking the substrate along the line of the propagated micro-
crack by applying a force on the substrate, wherein the aqueous
surfactant solution enters the micro-crack prior to the breaking
act.

12. (New) The method of breaking a substrate of brittle material according to claim 11, wherein the aqueous surfactant solution is selected to bond to broken substrate bonds in the micro-crack.

13. (New) The method of breaking a substrate of brittle material according to claim 11, wherein the aqueous surfactant solution further comprises air mixed with the aqueous surfactant solution.

14. (New) The method of breaking a substrate of brittle material according to claim 11, wherein the concentration of the aqueous surfactant solution is in the range of 0.01 to 1% of weight.

15. (New) The method of breaking a substrate of brittle material according to claim 11, wherein the aqueous surfactant solution comprises a cationic surfactant.

16. (New) The method of breaking a substrate of brittle material according to claim 15, wherein the cationic surfactant comprises cetyl trimethyl ammonium bromide (CTAB).

17. (New) The method of breaking a substrate of brittle material according to claim 11, wherein the aqueous surfactant solution comprises a nonionic surfactant.

18. (New) The method of breaking a substrate of brittle material according to claim 17, wherein the nonionic surfactant comprises octadecyl deca(ethylenoxide) hydroxide.

19. (New) The method of breaking a substrate of brittle material according to claim 11, wherein the aqueous surfactant solution comprises an anionic surfactant.

20. (New) The method of breaking a substrate of brittle material according to claim 19, wherein the anionic surfactant comprises dodecylbenzene sulfonic acid sodium salt.